

Magnetic properties of $\text{UCo}_{1-x}\text{Os}_x\text{Al}$ solid solutions: transition from itinerant metamagnetism to ferromagnetism

講師 : Alexander V. Andreev

(Institute of Physics, Academy of Sciences, Prague, Czech Republic)

日時 : 2018 年 10 月 3 日 (水) 15:00-

場所 : 先端物質科学研究科 402N

UCoAl belongs to a UTX family (T is a late transition metal of 3d, 4d or 5d series, X is a p-metal Al, Ga, In or Sn) with the hexagonal crystal structure of the ZrNiAl type. In magnetic field of 0.7 T applied along the c-axis, UCoAl undergoes a metamagnetic transition to a forced ferromagnetic state [1]. The ground state of UCoAl is paramagnetic [2], so it has to be classified as itinerant metamagnet with uniquely low critical field H_{cr} of the transition. Due to so low H_{cr} value, UCoAl is extremely sensitive to any influence like dilution of the U sublattice, external pressure or substitution. When Co is substituted by T = Fe, Ru, Rh and Ir in the $\text{UCo}_{1-x}\text{T}_x\text{Al}$ systems, H_{cr} rapidly decreases and already 1-2% doping stabilizes spontaneous ferromagnetism. Opposite, for T = Ni, Pd and Pt, H_{cr} increases and paramagnetism is stabilized.

Influence of only one of late d metal, Os, on the metamagnetism in UCoAl was not studied previously due to metallurgical problems (melting temperature of Os exceeds evaporation temperature of Al). Now we solved these problems, prepared $\text{UCo}_{1-x}\text{Os}_x\text{Al}$ solid solutions and studied their crystal structure and magnetic properties.

Terminal compound UOsAl does not form the ZrNiAl-type structure but hexagonal Laves phase of the MgZn_2 type. It is temperature-independent paramagnet, similar to the isostructural compound UFeAl. No field-induced transition is observed in fields up to 60 T. $\text{UCo}_{1-x}\text{Os}_x\text{Al}$ solid solutions with $x < 0.2$ have the ZrNiAl crystal structure. The compound with $x = 0.2$ has traces (~2%) of an impurity phase, so we consider this Os content as a homogeneity limit.

Magnetization measurements performed on single crystals (except for $x = 0.2$, this alloy was studied on isotropic polycrystal) showed that compounds with $x \geq 0.01$ are ferromagnets. Spontaneous moment increases from 0.32 $\mu_B/\text{f.u.}$ at $x = 0.01$ to 0.55 $\mu_B/\text{f.u.}$ at $x = 0.20$, which is almost twice larger than the magnetic moment induced at the metamagnetic transition in UCoAl. T_C increases from 16 K at $x = 0.01$ to 54 K at $x = 0.20$. All the compounds within the homogeneity range exhibit strong field and thermal hysteresis. At very low Os content, $\text{UCo}_{0.998}\text{Os}_{0.002}\text{Al}$, the ground state of the compound is still metamagnetic like in UCoAl. Transition field at 2 K is 0.35 T, which is already as twice as lower than that in UCoAl. H_{cr} increases with increasing temperature in the same way as in UCoAl. $\text{UCo}_{0.995}\text{Os}_{0.005}\text{Al}$ has almost purely ferromagnetic ground state with small metamagnetic component. It has $M_s = 0.3 \mu_B$ and $T_C = 8$ K. The ferromagnetism can be suppressed completely by external hydrostatic pressure of only 0.1 GPa. $\text{UCo}_{0.99}\text{Os}_{0.01}\text{Al}$ is already a pure ferromagnet with $T_C = 16$ K and $M_s = 0.32 \mu_B$. All compounds within the homogeneity range exhibit huge uniaxial magnetic anisotropy. The anisotropy field, defined as the field where the hard-axis curve reaches M_s value (or M just above metamagnetic transition in the case of metamagnets), is at least 120-130 T.

[1] A.V. Andreev, R.Z. Levitin, Yu.F. Popov, R.Yu. Yumaguzhin, Sov. Phys. Solid State, **27**, 1145 (1985).

[2] V. Sechovský, L. Havela, F.R. de Boer, J.J.M. Franse, P.A. Veenhuizen, J. Šebek, J. Stehno, A.V. Andreev, Physica B, **142**, 283 (1986).

5 研究科共同セミナーの認定科目です

担当 : 石井 勲 (先端物質科学研究科) ・内線 7042



【世話人】
高根 美武 (内 7653) 浴野 稔一 (内 6552)
松村 武 (内 7021) 木村 昭夫 (内 7471)
犬丸 啓 (内 7741)
【広報担当】
稲垣 (内 5720)

